

Technical Data Sheet

Unicoate Epoxy Topcoat

UE 2980

Description:

A two-component pigmented Epoxy Topcoat for the general use of internal concrete, steel, and metal works.

Surface Preparation and Application Method:

1. The surface should be dry, and free from dirt, oil, grease, and powdery material.
2. Sand the entire surface until completely smooth.
3. For steel apply two coats of **Unicoate Zinc Phosphate Epoxy Primer/** by cross-coat technique in order to obtain a high build and ensure optimum spreading. For concrete two coats of **Unicoate Epoxy Sealer** or **Unicoate Epoxy Primer**.
4. Allow Three (3) minutes to flash off between coats.
5. Fill holes and cracks with **Unicoate** epoxy filler.
6. After drying, sand the surface until completely smooth.
7. Apply two coats of Unicoate Epoxy Topcoat Matt.

Features:

1. Excellent alkali resistance
2. Excellent coverage
3. Excellent mechanical and abrasion resistance.

Dilution and Application:

Type of Hardener	: Unicoate EXH333
Type of thinner	: Unicoate E850
Percentage of thinning	: 5 – 10 % by volume
Mixing ratio	: 3.5 Part A : 1 Part B
Nozzle orifice	: 1.5 - 2 mm Pot
Life (after mixing at 25C)	: 4-5 hours
Output pressure	: 3 - 4 bar
Tools	: Air spray gun

Unicoate Epoxy Topcoat Gloss can be also used by roller.

Drying time (at 25C):

Touch dry	: 3-4 hours
Hard dry	: 8-10 hours

UNICOATE FOR INDUSTRY
New industrial Area-Doha Qatar

TEL: +974-4039927; Email: info@unicoate.com www.unicoate.com

Physicals Properties:

Finish	: Gloss
Flash Point	: 25 C
Specific Gravity	: 1.20 – 1.25 Kg/L Part A : 0.95-0.98 Part B
Solid by Weight	: 60 - 70% Part A : 45-50% Part B
Coverage rate	: 10 - 12m ² /L
Dry film thickness	: 40 - 50 microns
Shelf Life (dry and cool store)	: One year

Packing:

14 Litter drum Part A + 4 Litter Part B,

3.0L Gallon Part A + 0.8 Litter Part B

Colors:

White, Grey, and other Colors.

Subsequent Coats:

None

Remarks:

Before Application

- Stir thoroughly
- Check Temperature above 7 C and relative humidity less than 80%

After Application

- Clean all tools used immediately with Epoxy Thinner
- Close the cans after use
- Store in a dry and cool area

For more information, don't hesitate to contact our Technical Department.

UNICOATE FOR INDUSTRY

New industrial Area-Doha Qatar TEL: +974-40399272 Email: info@unicoate.com

www.unicoate.com